

**Item No. 210S
Flexible Base**

210S.1 Description

This item governs furnishing and placing a crushed stone base course for surfacing, pavement, or other base courses. "Flexible Base" shall be constructed on an approved, prepared surface in one or more courses conforming to the typical sections and to the lines and grades, indicated on the Drawings or established by the Engineer or designated representative.

This specification is applicable for projects or work involving either inch-pound or SI units. Within the text and accompanying tables, the inch-pound units are given preference followed by SI units shown within parentheses.

210S.2 Submittals

The submittal requirements of this specification item may include:

- A. Source, gradation and test results for the crushed limestone material,
- B. Notification that the crushed limestone stockpile is completed and ready for testing, and
- C. Field density test results for in-place compacted flexible base,

210S.3 Material

A. Mineral Aggregate

The material shall be crushed argillaceous limestone meeting the requirements specified herein. The material shall be from sources approved by the City and shall consist of durable crushed stone that has been screened to the required gradation.

Flexible base materials shall be tested according to the following TxDOT standard test methods:

a) Preparation for Soil Constants and Sieve Analysis	Tex-101-E
b) Liquid Limit	Tex-104-E
c) Plastic Limit ¹	Tex-105-E
d) Plasticity Index	Tex-106-E
e) Sieve Analysis	Tex-110-E
f) Wet Ball Mill ²	Tex-116-E
g) Triaxial Test	Tex-117-E, Part II

- 1. Plasticity Index shall be determined in accordance with Tex-107-E (Linear Shrinkage) when liquid limit is unattainable as defined in Tex-104-E.
- 2. When a soundness value is required on the drawings, the material shall be tested in accordance with Tex-411-A.

Base material shall be stockpiled after crushing, then tested by the City's designated laboratory and approved by the Engineer or designated representative prior to being hauled to the Project.

The material shall be well graded and shall meet the following requirements:

* See Modifications for additional information

Sieve Designation		Other Requirements	% Retained
US	SI		
1 3/4"	45 mm		0
7/8"	22.4 mm		10-35
3/8"	9.5 mm		30-50
#4	4.75 mm		45-65
#40	425 µm		70-85
		Maximum Plasticity Index	10
		Maximum Wet Ball Mill	42
Maximum Increase in passing #40 (425 µm) sieve from Wet Ball Mill Test			20

Minimum compressive strength when subjected to the triaxial test shall be 35 psi at 0 psi lateral pressure [240 kiloPascal (kPa) at 0 kPa lateral pressure] and 175 psi at 15 psi lateral pressure [1200 kiloPascal (kPa) at 100 kPa lateral pressure].

B. Asphaltic Material

Prime Coat. Prime Coat shall conform to the requirements of Standard Specification Item 306S, "Prime Coat", except for measurement and payment.

210S.4 Stockpiling, Storage and Management

A. Managing Material:

The stockpile shall be constructed on a relatively smooth area that has been cleared of debris, weeds, brush, trees and grass. Stockpiles shall contain between 25,000 and 50,000 cubic yards (19,100 to 38,200 cubic meters). The stockpile shall be constructed using scrapers, bottom dumps or other similar equipment that allows dumping and spreading without rehandling. The stockpile shall be constructed to allow dumping and spreading in one direction only. The height of the stockpile shall not exceed the capabilities of available equipment to make a full cut (bottom to top) on any of the four sides.

A stockpile shall be completed before being tested by the City. The Contractor's supplier shall notify the City when a stockpile has been completed and is ready to be tested. The stockpile shall not be added to after it has been tested.

The Contractor shall provide material only from stockpiles that have been inspected, tested and accepted by the City. A ticket showing the date, source, stockpile number, and net weight (mass) shall be provided to the Inspector with each load of material delivered to the Project.

Material shall be loaded from the stockpile by making successive vertical cuts through its entire depth.

B. Test Sampling:

The Contractor's supplier may choose the method of sample gathering for testing by the City's laboratory as follows:

1. The supplier shall make a full-height cut a sufficient distance into each side of the stockpile to obtain a uniform sample. The four samples (one from each side of the stockpile) shall then be combined and mixed into a single "test" specimen from which the City's laboratory can obtain a sample.
2. As the stockpile is constructed, a perpendicular cut will be made across the spreading direction at every two feet to four feet (0.6 to 1.2 meters) of height and the sample used to start a "mini" stockpile. The process shall be repeated in two feet to four feet (0.6 to 1.2 meter) increments of height, until the stockpile and the "mini" stockpile are completed. Samples shall be obtained from the "mini" stockpile in the same manner described in (1) above.

C. Testing and Acceptance:

When initial tests indicate that the material is unacceptable, the City may, if requested by the Contractor's supplier, sample and test the material one more time. The additional sampling and testing shall be paid for by the supplier.

210S.5 Construction Methods

A. Preparation of Subgrade:

Flexible base shall not be placed until the Contractor has verified by proof rolling that the subgrade has been prepared and compacted in conformity with Standard Specification Item 201S, "Subgrade Preparation," to the typical sections, lines and grades indicated on the Drawings. Any deviation shall be corrected and proof rolled prior to placement of the flexible base material.

The Contractor shall not place flexible base until the subgrade has cured to the satisfaction of the Engineer or designated representative, regardless of whether or not the subgrade has been successfully proof rolled. As a minimum, this will be after the surface displays no damp spots and there is no evidence of "sponginess" in the subgrade.

B. First Lift:

Immediately before placing the flexible base material, the subgrade shall be checked for conformity with grade and section. The thickness of each lift of flexible base shall be equal increments of the total base depth. No single lift shall be more than six inches (150 mm) or less than three inches (75 mm) compacted thickness.

The material shall be delivered in approved vehicles. It shall be the responsibility of the Contractor to deliver the required amount of material. If it becomes evident that insufficient material was placed, additional material as

necessary shall be delivered and the entire course scarified, mixed and compacted.

Material deposited upon the subgrade shall be spread and shaped the same day unless otherwise approved by the Engineer or designated representative. In the event inclement weather or other unforeseen circumstances render spreading of the material impractical, the material shall be spread as soon as conditions allow.

Additionally, if the material cannot be spread and worked the same day it is deposited, the Contractor shall "close up" the dump piles before leaving the job site. "Closed up" shall be defined as the use of a motor grader to blade all dump piles together, leaving no open space between piles.

The material shall be spread, sprinkled, if required, then thoroughly mixed; bladed, dragged and shaped to conform to the typical sections indicated on the Drawings.

All areas and "nests" of segregated coarse or fine material shall be corrected or removed and replaced with well-graded material.

* See Modifications for additional information

~~Each lift shall be sprinkled as required to bring the material to optimum moisture content,~~ then compacted to the extent necessary to provide not less than the percent density specified in Section 210S.5.D, "Density." In addition to the requirements specified for density, the full depth of flexible base material shall be compacted to the extent necessary to remain firm and stable under construction equipment. After each section of flexible base material is completed, tests, as necessary, will be made by the Engineer or designated representative. As a minimum, three in-place density tests per section per day will be taken. If the material fails to meet the density requirements, it shall be reworked as necessary to meet these requirements. All initial testing will be paid for by the City. All retesting shall be paid for by the Contractor.

Throughout the entire operation, the surface of the material shall be maintained by blading and, upon completion, shall be smooth and shall conform to the typical section indicated on the Drawings and to the established lines and grades.

In that area on which pavement is to be placed, any deviation in excess of 1/4 inch (6.5 mm) in cross section or 1/4 inch in a length of 16 feet (6.5 mm in a length of 5 meters) measured longitudinally shall be corrected by loosening, adding or removing material, and by reshaping and recompacting. All irregularities, depressions or weak spots shall be corrected immediately by scarifying the areas affected, adding suitable material as required, and by reshaping and recompacting. Should the lift, due to any reason or cause, lose the required stability, density and/or finish before the surfacing is complete, it shall be recompacted and refinished at the Contractor's expense.

C. Succeeding Lifts:

Construction methods for succeeding lifts shall be the same as prescribed for the first lift. For that lift of the flexible base upon which the curb and gutter will be constructed, as well as the last flexible base lift (i.e. top of the flexible base), the Contractor shall check the surface of the lift for conformity to the lines and grades by setting "blue tops" at intervals not exceeding 50 feet (15 meters) on

the centerline, at quarterpoints, at curb lines or edge of pavement, and at other points that may be indicated on the Drawings.

When the thickness of a particular lift of the flexible base is in question, the Contractor shall check the surface of the lift for conformity to the lines and grades by setting "blue tops" at intervals not exceeding 50 feet (15 meters) on the centerline, at quarter points, at curb lines or edge of pavement, and at other points that may be indicated on the Drawings

D. Density:

The flexible base shall be compacted to not less than 100 percent density as determined by TxDOT Test Method Tex-113-E.

Field density determination shall be made in accordance with TxDOT Test Method Tex-115-E unless otherwise approved by the Engineer or designated representative. Each lift of the flexible base shall also be tested by proof rolling in conformity with Standard Specification Item 236S "Proof Rolling."

E. Priming: * See Modifications for additional information

After the flexible base material has been compacted to not less than 100 percent density, and tested by proof rolling, a prime coat will be applied in accordance with Standard Specification Item 306S, "Prime Coat."

F. Curing:

Pavement materials, such as a tack coat or surface course, shall not be placed on the primed surface until the prime coat has been absorbed into the base course. At least 24 hours, or longer if designated by the Engineer or designated representative, shall be allowed when cutback asphalt is used as the prime coat.

210S.6 Measurement

"Flexible Base" will be measured by the cubic yard (cubic meter: 1 cubic meter equals 1.196 cubic yards), complete in place, as indicated in the Contract Documents.

210S.7 Payment

This item will be paid for at the contract unit bid price for "Flexible Base". The unit bid price shall include full compensation for all work specified herein, including the furnishing, hauling, placing and compacting of all materials; for rolling, proof rolling, recompacting and refinishing; for all water required; for retesting as necessary; for priming; and for all equipment, tools, labor and incidentals necessary to complete the Work.

Prime coat will not be measured and paid for directly but shall be included in the unit price bid for Standard Specification Item 210S, "Flexible Base."

Payment will be made under one of the following:

Pay Item No. 210S-A: Flexible Base Per Cubic Yard.

End

<i>SPECIFIC</i> CROSS REFERENCE MATERIALS
--

City of Austin Standard Specifications

<u>Designation</u>	<u>Description</u>
Item No. 201S	Subgrade Preparation
Item No. 236S	Proof Rolling
Item No. 306S	Prime Coat

Texas Department of Transportation: Standard Specifications for Construction and Maintenance of Highways, Streets, and Bridges

<u>Designation</u>	<u>Description</u>
Tex-101-E	Preparation of Soil and Flexible Base Materials for Testing
Tex-104-E	Determination of Liquid Limit of Soils
Tex-105-E	Determination of Plastic Limit of Soils
Tex-106-E	Method of Calculating the Plasticity Index of Soils
Tex-107-A	Determination of Bar Linear Shrinkage of Soils
Tex-110-E	Determination of Particle Size Analysis of Soils
Tex-113-E	Laboratory Compaction Characteristics and Moisture-Density Relationship of Base Materials and Cohesionless Sands
Tex-115-E	Field Method for Determination of In-Place Density of Soils and Base Materials
Tex-116-E	Ball Mill Method for Determination of the Disintegration of Flexible Base Material
Tex-117-E Materials	Triaxial Compression Tests for Disturbed Soils and Base Materials
Tex-411-A	Soundness of Aggregate By Use Of Sodium Sulfate Or Magnesium Sulfate

<i>RELATED</i> CROSS REFERENCE MATERIALS

City of Austin Standard Details

<u>Designation</u>	<u>Description</u>
No. 1000S-2	Flexible Base with Asphalt Surface Trench Repair-Existing Pavement
No. 510S-3	Typical Trench with Paved Surface
No. 1000S	Bus Stop Paving
No. 1000S-10	Local Street Sections
No. 1000S-11(1)	Residential and City of Austin Neighborhood Collector Street Sections
No. 1000S-11(2)	Industrial and Commercial Collector Street Sections
No. 1000S-12(1)	Primary Collector Street Sections
No. 1000S-12(2)	Primary Arterial Street Sections
No. 1000S-13(1)	Minor Arterial Street Sections (4 Lanes)
No. 1000S-13(2)	Minor Arterial Street Sections-(4 Lanes divided)
No. 1000S-14	Major Arterial Street Sections

City of Austin Utility Criteria Manual

<u>Designation</u>	<u>Description</u>
Section 5.8.2	Flexible Base
Section 5.7.3	Flexible Base with Asphalt Surface
Section 5.9.1	Excavation in Alley

City of Austin Transportation Criteria Manual

<u>Designation</u>	<u>Description</u>
Section 3.2.0	General Criteria
Section 3.4.3 .D	Layer Data-Minimum Thickness
Table 3-1	Minimum Layer Thickness
Section 3.4.3 .F	Layer Data- Minimum Thickness
Table 3-2	Layer Thickness Increment
Section 3.4.3 .J	Layer Data- Stiffness Coefficient
Table 3-3	Stiffness Coefficient
Table 3-9	Recommended Salvage values
Table 3-10	AASHTO Layer Coefficients